

WearGuard™ D-A SYN 2000 Series is specially formulated with ChemGuard™ PAO additive technology system. Under normal operating conditions you can expect extended drain cycles and experience 6,000 to 8,000 hours of use in rotary screw and rotary vane compressors.

WearGuard™ D-A SYN 2000 Series is based on a very thermally and oxidatively stable PAO (polyalphaolefin) base oil for use in a wide variety of air compressors. WearGuard™ D-A SYN 2000 Series is used where maximum seal, paint, plastic, and rubber compatibility is required.

WearGuard™ D-A SYN 2000 Series is formulated to resist varnish under high temperature applications and minimize impact from airborne contaminants.

Applications

- Rotary Screw
- Reciprocating
- Rotary Vane

Characteristics

- Outstanding thermal and oxidative stability
- Compatible with most seals, plastics, rubbers
- Wide operating temperature range
- Non-detergent
- Anti-wear protection
- Compatible with most compressor oils
- High flash point means increased safety
- Extended drain intervals

Typical Properties

WearGuard™ D-A SYN 2000 Series	ASTM Method	WearGuard D-A SYN 2032	WearGuard D-A SYN 2046	WearGuard D-A SYN 2068	WearGuard D-A SYN 2100	WearGuard D-A SYN 2150
ISO Viscosity Grade	D2422	32	46	68	100	150
Viscosity, cSt, 40° C/100° C	D445	32 / 5.5	46 / 7.5	68 / 9.5	100 / 14.5	150 / 18.3
Viscosity Index	D2270	140	128	135	150	131
Pour Point, °C/°F	D97	-54 / -65	-51 / -60	-48 / -55	-45 / -50	-45 / -50
Flash Point, °C/°F	D92	221 / 430	244 / 465	241 / 465	246 / 475	260 / 500
Four Ball Wear 40kg, 1200rpm @ 75° C	D4172	0.43mm	0.43mm	0.43mm	.44mm	–
Foaming Sequences I, II, III	D892	Nil	Nil	Nil	Nil	Nil
Copper Corrosion	D130	1B	1B	1B	1B	1B
Specific Gravity	D1298	0.85	0.86	0.86	0.86	0.86



801 Edwards Drive - Lebanon, IN 46052
1-800-OIL-LUBE (1-800-645-5823)
(317) 923-5321 (765) 482-3065 FAX
www.dalube.com dalube@dalube.com

DA-SCO2000 rev 9/2013

The information in this bulletin is, to the best of our knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control.

© 2013, D-A Lubricant Company, Inc.